



INFORMAÇÕES TÉCNICAS

PVC RÍGIDO

| NAME OF THE STANDARD | UNIT | STANDARD |
|------------------------------------|------------------------|------------------------|
| Specific Gravity | g/m ³ | 1.5-1.55 |
| Tensile Strength | Mpa | ≥52.0 |
| Rate of change at heating | (Lenght and Breadth) % | Breadth ≤ 3 Lenght ≤ 5 |
| Impact | kJ/m ² | ≥ 5.0 |
| Weika softening point | °C | ≥ 80 |
| Corrosion Degree 60° ± 2°C 5h | G/m ² | |
| 40%NaOH | - | - 1.0 ~ + 1.0 |
| 40% HNO ₃ | - | - 1.0 ~ + 1.0 |
| 30% H ₂ SO ₄ | - | - 1.0 ~+ 1.0 |
| 35%HCL | - | - 2.0 ~+ 2.0 |

The information is give in good faith, and is based on our general experience, because of the many particular factors which are outside our knowledge and control that affect the use of products, no warranty is given or is to be implied. Freedom from patent rights must not be assumed.